



Thermoplastic Single Ply and Multi-Ply Roofing Systems

2670 Leisz's Bridge Road, Suite 400, Leesport, PA 19533 Phone (610) 916-9500 Fax (610) 916-9501

FLEX ISO-II and FLEX ISO-III ROOF INSULATION TECHNICAL DATA SHEET

PRODUCT DESCRIPTION

FLEX ISO-II is a closed-cell, polyiso foam core integrally laminated to heavy black (non-asphaltic), fiber-reinforced felt facers. FLEX ISO-II is offered in a variety of thicknesses, providing long-term thermal resistance (LTTR) values from 6.0 to 25.0.

FLEX ISO-III is a closed-cell, polyiso foam core integrally laminated to heavy coated-glass facers that are durable and dimensionally stable. FLEX ISO-III is offered in a variety of thicknesses, providing long-term thermal resistance (LTTR) values from 6.0 to 25.0.

Recycled Content: Between 16% and 43% by weight, depending on thickness (55% post-consumer, 45% post-industrial).

Both products are available in 25-psi formula. Available in 4'x4' (1220mm x 1220mm) and 4'x8' (1220mm x 2440mm) panels.

TECHNICAL DATA

Thickness		LTTR* Value	RSI**	PCS/PKG	Metal Deck Flute Spanability	
In	mm				In	mm
1.0	25.40	6.0	1.06	46	2.625	66.68
1.5	38.10	9.0	1.58	31	4.375	111.13
2.0	50.80	12.1	2.13	23	4.375	111.13
2.5	63.50	15.3	2.69	18	4.375	111.13
3.0	76.20	18.5	3.26	15	4.375	111.13
3.5	88.90	21.7	3.82	13	4.375	111.13
4.0	101.60	25.0	4.40	11	4.375	111.13

*LTTR values of the foam were determined in accordance with CAN/ULC-5770 and ASTM-C1289, Annex A1. Samples were third-party selected by an accredited material testing laboratory. The LTTR results were reviewed and authorized by FM Approvals and certified by the PIMA Quality Mark Program.

** RSI is the metric expression of R-value (m²xK/W). To calculate the RSI, multiply the LTTR-value by .176.

RECOMMENDED USES

FLEX ISO-II is typically specified for hot asphalt applications of Flex Modified Bitumen and Flex Thermoplastic Single Ply Membrane Systems. FLEX ISO II has one side marked for hot BUR and modified bitumen and one unmarked side for single ply and cold applied modified bitumen, making this an adaptable product suitable for a variety of applications.

FLEX ISO-III is typically specified for cold applied Flex Modified Bitumen and Flex Thermoplastic Single Ply Membrane Systems. **Do not use this product with hot applied roofing systems.**

INSTALLATION

Before installation begins, the roof deck should be firm, well attached, even, clean and dry. Proper attachment of the insulation is necessary to prevent roof failures. Flex is not responsible for any damage caused by improper attachment. Flex iso products can be attached to decks that are approved by FM Approvals and local codes. Flex is not responsible for determining the suitability of the deck. Flex ISO products shall be kept dry before, during and after installation. Install only as much Flex roof insulation as can be covered the same day with completed roofing. Although Flex ISO has been designed to withstand normal foot traffic, protection from damage by construction traffic and/or abuse is extremely important. Roof surface protection such as plywood shall be used in areas where storage and staging are planned and heavy or repeated traffic is anticipated during or after installation. A two layer application of Flex ISO is strongly recommended. The joints in each layer should be offset in order to avoid a vertically continuous joint through the total insulation thickness. Two layers (or more) with joints staggered can provide improved insulation performance by eliminating thermal bridges. This method also reduces condensation potential and thermal stress on the roof membrane. Mechanical fastening is the recommended method of attachment over nailable decks such as steel or wood. Flex ISO II may be installed to a structural concrete deck with hot bitumen or Flex Deck Insulation Adhesive. For further recommendations regarding attachment please contact Flex Technical Services.

PHYSICAL PROPERTIES

<u>Property</u>	<u>Test Method</u>	<u>Typical Results</u>
Dimensional Stability	ASTM D 2126	<2%
Compressive Strength (10% Deformation)	ASTM D 1621	20 psi (138 kPa) 25 psi (172 kPa)
Water Absorption	ASTM C 209 ASTM D 2842	<1% <3.5%
Moisture Vapor Transmission	ASTM E 96	< 1.5 perm (85.0ng/(Pa•s•m ²))
Product Density	ASTM D 1622	Nominal 2.0 pcf (32.02 kg/m ³)
** Flame Spread	ASTM E 84 (full 10 min. test)	<75**
Smoke Developed	ASTM E 84 (full 10 min. test)	50-170**
Tensile Strength	ASTM D 1623	>730 psf (35 KPa)
Service Temperature		-100 to 250°F (-73 to 122°C)

** The numerical ratings as determined by ASTM Test Method E84 are not intended to reflect hazards presented by this or any other material under actual fire conditions. A flame spread index of 75 or less and smoke development of 450 or less meet code requirements regarding flame spread and smoke development for foam plastic roof insulation.

However the codes exempt foam plastic insulation when used in roof deck constructions that comply as an assembly with FM 4450 or UL 1256 (see IBC, NBC, UBC, and SBS Sections on Foam Plastic Insulation (Chapter 26). Smoke development does not apply to roofing.

The physical properties listed above are presented as typical average values as determined by accepted ASTM test methods and are subject to normal manufacturing variation.

STORAGE

Factory applied packaging is intended only for protection during transit. When stored outdoors or on the job site the insulation should be stacked on pallets at least four inches above ground level and be completely covered with a weatherproof covering such as a tarpaulin. The temporary factory applied packaging should be slit or removed to prevent accumulation of condensation. Roof insulation that has become wet or damaged should be removed and replaced with solid, dry insulation.

CAUTION

DO NOT LEAVE EXPOSED This product is a polyiso organic plastic foam and will burn if exposed to an ignition source of sufficient heat and intensity, or open flame, such as a welders torch. Like other organic materials this product will release smoke if ignited. Do not apply flame directly to Flex Roof Insulations. This product should be used only in strict accordance with Flex's recommended uses and application instructions.

LIMITATION OF LIABILITY

Other than the aforementioned representations and descriptions, Flex Membrane International, Inc. (hereafter, "Seller") makes no other representations or warranties as to the insulation sold herein. The Seller disclaims all other warranties, express or implied, including the warranty of merchantability and the warranty of fitness for a particular purpose. Seller does however have a limited warranty as to the LTTR-value of the insulation, the terms of which are available upon request from the Seller. The Seller shall not be liable for any incidental or consequential damages including the cost of installation, removal, repair, or replacement of this product. The Buyer's remedies shall be limited exclusively to, at Seller's option, the repayment of the purchase price or resupply of product manufactured by Flex in a quantity equal to that of the nonconforming product. Flex distributors, agents, salespersons or other independent representatives have no authority to waive or alter the above limitation of liability and remedies.