



Thermoplastic Single Ply and Multi-Ply Roofing Systems

2670 Leisch's Bridge Road, Suite 400, Leesport, PA 19533 Phone: 610-916-9500 Fax: 610-916-9501

FLEX 180N GEOTEXTILE SEPARATION LAYER

Flex 180N Geotextile is a non woven geotextile composed of polypropylene fibers, which are formed into a stable network such that the fibers retain their relative position. Flex 180N Geotextile is inert to biological degradation and resists naturally encountered chemicals, alkalis, and acids.

The Flex 180N Geotextile is installed as a separation or protection layer in Flex Protected Membrane Roof Systems. It also is used as a protection layer and filtration fabric in Flex Garden Roof Systems and Flex Below Grade Waterproofing Systems. The Flex 180N has excellent physical and hydraulic properties in addition to high tensile strength. The Flex 180N provides the required strength and abrasion resistance to protect Flex Thermoplastic Roofing and Waterproofing Membranes withstanding installation and application stress to create an effective, long term solution.

TECHNICAL DATA

<u>SPECIFICATION</u>	<u>TEST METHOD</u>	<u>VALUE</u>
Thickness	ASTM D 5199	.090"
Weight	ASTM D 5261	8.2 oz/yd
Dimensions		15'x300'
Tensile Strength	ASTM D 4632	205lbs x 205lbs
Tensile Elongation	ASTM D 4632	50%
Tear Strength	ASTM D 4533	80lbs x 80lbs
Mullen Burst Strength	ASTM D 3786	380 psi
Puncture Strength	ASTM D 4833	130 lbs
Apparent Opening Size	ASTM D 4751	80 US Sieve
Permittivity	ASTM D 4491	1.2 sec ⁻¹
Permeability	ASTM D 4491	0.21 cm/sec
Flow Rate	ASTM D 4491	95 gal/min/ft ²
UV Resistance (500 hrs)	ASTM D 4355	70%

Disclaimer: Flex Membrane International, Inc. assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. Flex Disclaims any and all express, implied, or statutory standards, warranties or guaranties, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.